



ROOFON

Eco-friendly, Waterproofing and Protective Coating
for Roofs, Walls and Concrete



PRODUCT DESCRIPTION

SUPERSHIELD ROOFON is a cold-applied, one-component, waterborne liquid coating designed for waterproofing and protecting roofs, walls, and concrete infrastructures. It forms a resilient barrier that waterproofs the substrate, shields it from weather and atmospheric degradation, and functions as a cool roof coating due to its reflective properties.

SUPERSHIELD ROOFON is formulated with **WAPELASTIC TECHNOLOGY**, which incorporates long-chain polyurethane macromolecules into a water-based medium to create a stable dispersion. This technology combines the high performance of polyurethane with the ease of application of a one-component, water-based coating. The result is an ecological, low-VOC, and environmentally friendly product. SUPERSHIELD ROOFON maintains its elasticity, bridging and sealing hairline cracks. Developed from a 100% aliphatic polyurethane dispersion, it offers excellent UV resistance and does not require an additional topcoat for UV protection.

RECOMMENDED USES

- Architectural and protective coatings for bridges, flyovers, tunnels, and other infrastructure
- Exposed roof waterproofing solutions in both new construction and refurbishment projects
- Exposed roofs with many details and complex geometry when accessibility is limited
- Cost-efficient life cycle extension of failing exposed roofs
- Reflective coatings to enhance energy efficiency by reducing cooling costs
- Side walls
- Slope roofs
- Parapet walls
- Protection of polyurethane foam insulation

Substrates: cementitious, brick, stone, metal, and existing bituminous membranes

FEATURES AND BENEFITS

- One-component, water-based, and VOC-compliant
- Excellent weather, UV light, and water resistance
- Forms a fully bonded, seamless coating without joints
- Excellent adhesion to most building materials
- Flexible coating that accommodates substrate movements and bridges cracks
- Water vapor permeable
- The waterproofed surface can take light foot traffic
- Provides high solar reflectance



Lease Life
to Man-Made
Structures

ROOFON

TECHNICAL DATA

General Characteristics		
PROPERTY	VALUE	
Color and Appearance	White - Liquid	
Service Temperature	-40°C to + 90°C	
VOC Content	<100g /l (Low VOC Content)	
Performance Characteristics		
TEST NAME	TEST METHOD	PERFORMANCE
Water Permeability	EN 1062-6	> SD 50m
Permeability to water vapour	EN ISO 7783-1,2	Class I SD< 5m
Elongation at Break	ASTM D412	> 600%
Tensile Strength	ASTM D412	> 11 N/mm²
Solar Reflectance	ASTM E 903-96	91%
Capillary Absorption and Permeability to water	EN 1062-3	W < 0.1
Strength of Adhesion to indirect traction	EN 1542	≥ 0.8 N/mm²
Thermogravimetry	EN ISO 11358	+5% of reference with respect to loss of mass @ 600°C
Infrared spectrum	EN 1767	Position and relative intensities of the main absorption band matches with reference



APPLICATION GUIDELINES

Surface Preparation

Careful surface preparation is essential for optimum finish and durability. The substrate to be applied with SUPERSHIELD ROOFON needs to be clean, dry, and sound, free of any contamination that may harmfully affect the adhesion of the membrane. The maximum moisture content should not exceed 8%. The substrate's compressive strength should be at least 25 MPa, and its cohesive bond strength should be at least 1.5 MPa. New concrete structures need to dry for at least 28 days. Old, loose coatings, dirt, oils, organic substances, and dust need to be removed by appropriate methods. Possible surface irregularities need to be smoothed. Any loose surface pieces and grinding dust need to be thoroughly removed. Repairs to the substrate, filling of joints, honeycombs, and voids, and surface leveling must be carried out using the appropriate SUPERSHIELD products. Contact SUPERSHIELD for further information.

Consumption

1 - 1.5 kg/m² applied in two or three layers. This coverage is based on application by roller onto a smooth surface in optimum conditions. Factors like surface porosity, temperature, and application method can alter consumption.

Priming

For prime absorbent and brittle surfaces like concrete, cement screed, mortar, plaster, and wood, prime with SUPERSHIELD ROOFON diluted with 10% to 20% clean water primer. For very brittle surfaces or demanding applications, prime with Supershield Wapprime and allow the primer coat to cure according to its technical specifications.

Application

Stir well before using. Pour SUPERSHIELD ROOFON onto the prepared or primed surface and lay it out

by roller or brush until all surfaces are covered. You can also use airless spray, allowing a considerable saving in manpower. After 6 to 24 hours, apply another layer of the SUPERSHIELD ROOFON. For demanding applications and better waterproofing results, apply a third layer of SUPERSHIELD ROOFON. Reinforce always with Supershield Refab at problem areas, like wall floor connections, chimneys, pipes, waterspouts, etc. To do that, apply to the still-wet SUPERSHIELD ROOFON a correctly cut piece of Supershield Refab, press it to soak, and saturate again with enough SUPERSHIELD ROOFON. Do not apply the SUPERSHIELD ROOFON over 0.5 mm of thickness (dry film) per layer.

For detailed application instructions with the SUPERSHIELD REFAB, contact SUPERSHIELD.

Curing

The SUPERSHIELD ROOFON coating should be air-cured for a minimum of 4 to 6 days and protected from water or rain for a minimum of 18 hours.

LIMITATIONS

- Do not apply the SUPERSHIELD ROOFON in negative (deg C) temperatures or when rain or frost is imminent in the next 48 hours. For best results, the temperature during application and curing should be between 5°C and 35°C. Low temperatures retard curing, while high temperatures speed up curing. High humidity may affect the final finish. Do not apply SUPERSHIELD ROOFON to substrates that have rising moisture. Always apply during periods of falling ambient and substrate temperatures. If applied during rising temperatures, spinholes may occur from rising and expanding air.
- SUPERSHIELD ROOFON is slippery when wet. To avoid slipperiness during wet days, sprinkle suitable aggregates onto the still-wet coating to create an anti-slip surface.



- Ensure that each coat of SUPERSHIELD ROOFON is totally dry and the surface is free of pin holes before applying further coats.
- Ensure that the applied SUPERSHIELD ROOFON has sufficient curing time before any such inclement weather is expected.
- Do not allow temporary ponding or moisture (dew, condensation, etc.) to remain between coats on any horizontal surfaces or until the final coating has totally cured. Brush or mop surface water away during this time.
- It is recommended to carry out adhesion and compatibility tests with the primer prior to the application of the following coats.
- SUPERSHIELD ROOFON should not be applied to roofs subject to long-term ponding water, especially with subsequent periods of frost. In cold climatic zones, for roofing structures with a pitch of less than 3%, appropriate drainage measures must be considered.
- SUPERSHIELD ROOFON should not be subject to permanent water immersion.
- While SUPERSHIELD ROOFON is resistant to most commonly encountered atmospheric pollutants, proprietary cleaning solutions, environmental spoilage, the suitability of the product for use in applications with increased chemical resistance requirements should first be established in consultation with SUPERSHIELD.

HEALTH AND SAFETY

SUPERSHIELD ROOFON contains chemicals that may cause skin irritation. For personal precaution, protective gloves and goggles are recommended to be worn during the handling of this product. If the product gets in contact with the eyes, flush immediately with clean water and seek medical assistance if symptoms persist.

STORAGE

SUPERSHIELD ROOFON pails should be stored in dry and cool rooms for up to 18 months. Protect the material against frost and direct sunlight.

Storage temperature: 5°C–30°C. Products should remain in their original, unopened containers.

PACKAGING

20 kg pails.

WARRANTY

Supershield warrants that its products will be free from material defects and will comply with the specifications provided in their respective technical data sheets. If any product is proven to be defective, Supershield's liability will be limited to the replacement of the product. Supershield will not be liable for any incidental or consequential damages. No other warranties, express or implied, shall apply, including warranties of merchantability or fitness for a particular purpose. It is the user's responsibility to determine the suitability of the product for their intended use and to assume all risks and liabilities associated with its application. Supershield reserves the right to alter the properties of its products without prior notice.